
7952 Nieman Road Lenexa, KS 66214-1560 USA




Type 1 reference block

Determination of sensitivity levels of penetrant systems

Art. no.: 127.400.001





Depth of notch is given by the thickness of the nickel-chromium layer. Transversal notches are produced by stretching the panel into longitudional direction.

The ratio *notch width*: *notch depth* is approx. 1:20 for each notch.

These panels are used for **determination of sensitivity** of fluorescent and color contrast penetrant systems.

A declaration of conformity of the respective reference block with EN ISO 3452-3 and an inspection certificate acc. to EN 10204, Type 3.1 B is attached.



Sensitivity levels:

Fluorescent penetrant

Level	Sensitivity	Plate
1	Normal	30 µm
2	High sensitive	20 μm
3	Ultra high sensitive	10 μm

Colour contrast penetrant

1	Normal	50 µm
2	High sensitive	30 µm