

Product Data Sheet

FP-923

Fluorescent Penetrant



Met-L-Chek Company manufactures a complete line of penetrants used in the fluorescent (**Type 1**) and visible (**Type 2**) dye penetrant inspection process. All Met-L-Chek Company penetrants are qualified to **AMS-2644** and are sold under the *Met-L-Chek*® and **Pen-Chek**® trademarks. Met-L-Chek Company products are manufactured under license in The Netherlands by NDT Europa.

FP-923 is approved to **AMS-2644** as a fluorescent (**Type 1**); Methods "A", and "C"; sensitivity level **3** water washable inspection penetrant. For Method "C" applications it is used with **E-59**, **E-59A**, **R-503**, and **R-504**. **FP-923** is applied by immersion, spray, or wipe on. It is approved for high sensitivity aerospace applications.

FP-923 is listed on the Qualified Products List for AMS-2644. It meets the requirements of AMS-2647, ASME Boiler and Pressure Vessel Code Section V, ASTM E-165, and ASTM E-1417, for penetrant inspection materials. It is low in sulfur and halogens and is safe for use on all metal surfaces.

Guide to METHOD "A" processing per ASTM E-1417

- 1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°-125°F) before penetrant is applied.
- 2. Apply **FP-923** penetrant using spray, immersion, or wipe on.
- 3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4°-10°C (40-50°F).
- 4. Wash part; water temperature $10^{\circ}-38^{\circ}C$ ($50^{\circ}-100^{\circ}F$). Water pressure < 275kPa (< 40 psi); if a hydro-air nozzle is used, limit pressure to < 172kPa (< 25 psi). Distance > 30cm (> 12 inches). Wash time- only long enough to remove surface fluorescence under UV-A (black light) .
- 5*. Dry part; temperature not to exceed 71°C (160°F), time only long enough to dry surface.
- 6. Apply dry powder developer, form "a" (**D-72A**), by dusting, or non aqueous developer, form "d"(**D-70**), by spraying.
- 6A*. If water based developer form "c"(**D-78B**) is used it is applied by immersion or spray, prior to step 5 drying.
- 7. Wait a minimum of 10 minutes before inspection. Maximum time is 1 hour for form "d" (non aqueous) and maximum 4 hours for form "a" (dry powder). If times are exceeded, clean part and reprocess.
- 8. Use UV-A illumination of >1000 μ W/cm² @ 15 inches (38.1 cm) in a darkened area of < 21 lux visible light (< 2 foot candles).

Guide to METHOD "C" (wipe off) processing per ASTM E-1417

- 1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°-125°F) before penetrant is applied.
- 2. Apply **FP-923** penetrant using spray, immersion, or wipe on.
- 3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4°-10°C (40-50°F).
- 4. Moisten cloth with **E-59**, **E-59A**, **R-503** or **R-504** and wipe penetrant from surface. **Do not** spray remover on surface to remove penetrant, as sensitivity will be impaired. Water may be used to wipe **FP-923** from the surface, but the surface must be dried before developer is applied.
- 5. Apply dry powder developer **D-72A** by dusting, or non aqueous developer **D-70** by spraying.
- 6. Wait a minimum of 10 minutes before inspection.
- 7. Inspect under UV-A illumination of >1000 μ W/cm² @ 15 inches (38.1 cm) in a darkened area of < 21 lux visible light (< 2 footcandles).

Fluorescent Penetrant Indication





Product Data Sheet

FP-923

Fluorescent Penetrant

Typical Physical Properties

Form: clear yellow green liquid

Density: 918 g/L

Flash Point: > 93°C (> 200°F)

Viscosity 11.3 mm²/s Water Tolerance:> 10 % Water Content: < 1 %

Fluorescent Brightness: (AMS-2644 requirement > 90 %) 117.7%

Corrosion of aluminum: none Corrosion of carbon steel: none Corrosion of magnesium: none Corrosion of stainless steel: none Corrosion of titanium: none

Chloride content: < 100 ppm (0.01%) Fluoride content: < 50 ppm (0.005%) Sodium content: < 100 ppm (0.01%) Sulfur content: < 100 ppm (0.01%)

Mercury: none VOC's: 0 g/L

Ozone layer depleting substances: none

PCB's: none

The warranty shelf life of the product is 5 years from date of batch approval.

Specifications

ASTM E-1417

AMS-2644 AMS-2647

ASME B & PV code Sec. V ASTM E-165

ISO-3452 P & W PMC # 4360-7 SPOP-82 R-R RPS-702 PMC Code 9

GHS Information

Danger GHS Hazard Statements:

H315 Causes skin irritation.

H318 Causes serious eye damage.

GHS Precautionary statements: P102: Keep out of reach of children.

P210: Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.

P261: Avoid breathing fumes/gas/mist/vapors/spray.

P273: Avoid release to the environment.

P280: Wear protective glove/clothing/eye protection/face

protection.

P284: İn case of inadequate ventilation wear respiratory protection.

Product Availability

12 x 400 mL (16oz) aerosol 1 pint (0.4L) can with dauber 1 gallon (3.7L) can

5 gallon (18.9L) pail 55 gallon (208L) drum

NSN#

1 gallon 6850-01-263-8430 5 gallon 6850-01-263-2263 55 gallon 6850-01-263-4056





GHS response statements:

IF INHALED: Remove person to fresh air and keep comfortable for breathing, get medical advice/attention if you feel unwell.

IF ON SKIN: Wash with plenty of water. If skin irritation occurs, get medical advice/attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easily to do. Continue rinsing, get medical attention.

IF SWALLOWED: Immediately call a poison center/doctor/physician.Do Not induce vomiting.

IF ON CLOTHING: Take off contaminated clothing and wash it before reuse.

Transport:

DOT- not regulated < 450 L or 119 Gal containers

IATA- not regulated IMDG- not regulated



Phone: 913-685-0675, Fax: 913-685-1125 e-mail: sales@ndtsupply.com, www.ndtsupply.com

