

Product Data Sheet

VP-30

Visible Penetrant



Met-L-Chek Company manufactures a complete line of penetrants used in the fluorescent (**Type 1**) and visible (**Type 2**) dye penetrant inspection process. All Met-L-Chek Company penetrants are qualified to **AMS-2644** and are sold under the *Met-L-Chek*® and **Pen-Chek**® trademarks. Met-L-Chek Company products are manufactured under license in The Netherlands by NDT Europa.

VP-30 is a visible (**Type 2**), water washable (Method **A**) and solvent removable (Method **C**) inspection penetrant. It is designed for use in general metalworking, welding, nuclear and automotive applications for surface flaw and through leak detection. **VP-30** has found wide use in the inspection of food and dairy processing equipment such as heat exchanges. Visible penetrants are not rated by sensitivity levels per **AMS-2644** but are considered approximately equal to level 1 fluorescent penetrants. 50μ discontinuities are readily detected and under controlled conditions 30μ size defects may be highlighted by visible penetrants. **ISO-3452** does rate visible penetrants by sensitivity level with #2 being the most sensitive. **VP-30** is a level 2 per this specifications requirements.

VP-30 is listed on the Qualified Products List for **AMS-2644**. It meets the requirements of **ASME Boiler and Pressure Vessel Code Section V**, **ASTM E-165**, **ASTM E-1417**, and **ISO-3452** for penetrant inspection materials. It is low in Sulfur, Chlorine, Fluorine and other Halogens, making it safe for use on Titanium and high Nickel alloys found in aerospace, medical and nuclear components.

Guide to METHOD "A" processing per ASTM E-1417

- 1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°-125°F) before penetrant is applied.
- 2. Apply **VP-30** penetrant using spray, immersion, or wipe on.
- 3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4°-10°C (40-50°F).
- 4. Wash part; water temperature 10°-38°C (50°-100 °F). Water pressure < 275kPa (< 40 psi); if a hydro-air nozzleis used limit pressure to < 172kPa (< 25 psi). Distance > 30cm (> 1 2 inches). Wash time- only long enough to remove surface penetrant under white light.
- 5. Dry part, time only long enough to dry surface.
- 6. Apply non-aqueous developer **D-70** by spraying. If water based developers **D-78B** is used it is applied by immersion or spray, <u>prior to step 5 drying</u>.
- 7. Wait a minimum of 10 minutes before inspection.
- 8. Use lighting of 1100 lux/m2 (100 footcandles) minimum.

Guide to METHOD "C" wipe off processing per ASTM E-1417

- 1. Part must be clean, dry and at a temperature of 4.4°-52°C (40°-125°F) before penetrant is applied.
- 2. Apply **VP-30** using spray, immersion, or wipe on.
- 3. Wait a minimum of 10 minutes; 20 minutes if temperature is 4.4° - 10° C (40- 50° F).
- 4. Moisten cloth with remover E-59, E-59A, R-503 or R-504 and wipe penetrant from surface. Do not spray remover on surface to remove penetrant, as sensitivity will be impaired.
- 5. Apply nonaqueous developer **D-70**, by spraying.
- 6. Wait a minimum of 10 minutes before inspection.
- 7. Use lighting of 1100 lux/m2 (100 footcandles) minimum.

Through Leak Method

For through leak testing the penetrant is applied to one side of the component and then developer is applied to the opposite side. Thickness of the component will effect the dwell time which may range from 10 minutes to 2 hours.

Step 1 clean surface Step 2 apply penetrant

Step 4 remove penetrant

Step 5 apply developer

Step 7 inspect

Method "C"















VP-30

Visible Penetrant

Product Availability

12 x 400mL(16oz) vol. aerosol net wt 310g (10.9oz)

NSN #'s

6850-01-267-7989

6850-01-223-2867

1 pint(0.4L) can with dauber

1 gallon (3.7L) metal can

1 gallon

5 gallon

5 gallon (18.9L) metal pail 55 gallon (208L) metal drum



Typical Physical Properties

Form: red liquid Density: 801 g/L

Flash Point: >62.2°C (>144°F)

Viscosity: 2.5 mm²/s
Water Tolerance: > 5%
Corrosion of aluminum: none
Corrosion of carbon steel: none
Corrosion of magnesium: none
Corrosion of stainless steel: none
Corrosion of titanium: none

Chloride content: < 100 ppm (< 0.01%) Fluoride content: < 50 ppm (< 0.005%) Sulfur content: < 150 ppm (< 0.015%)

Mercury: none VOC's: 533 g/L

Ozone layer depleting substances: none

PCB's: none

The warranty shelf life of the product is 5 years from date of batch approval.

Specifications

AMS-2644
ASME B & PV code Section V
ASTM E-165
ASTM E-1417
Dassault IQ-1-0-1-20
ISO-3452
NAVSEA-T9074-AS-GIB-010/271
PMUC
RCC-M rev 2000





GHS Information

GHS Hazard Statements:

H227: Combustible liquid. H304: May be fatal if swallowed and enters airways.

Danger

H315: Causes skin irritation.

H318: Causes serious eye damage.

H336: May cause drowsiness or dizziness.

GHS Precautionary statements:

P102: Keep out of reach of children.

P210: Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.

P261: Avoid breathing dust/fumes/gas/mist/vapors/spray.

P264: Wash skin thoroughly after handling.

P271: Use only outdoors or in well-ventilated area.

P273: Avoid release to the environment.

P280: Wear protective glove/clothing/eye protection/face protection.

P284: In case of inadequate ventilation wear respiratory protection.

See SDS for full health and safety information

GHS response statements:

IF INHALED: Remove person to fresh air and keep comfortable for breathing, get medical advice/attention if you feel unwell.

IF ON SKIN: Wash with plenty of water. If skin irritation occurs, get medical advice/attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easily to do. Continue rinsing, get medical attention.

IF SWALLOWED: Immediately call a poison center/doctor/physician. Do Not induce vomiting.

IF ON CLOTHING: Take off contaminated clothing and wash it before reuse.

Transport:

DOT- not regulated < 450 L or 119 Gal containers IATA- not regulated

IMDG- not regulated





